



Shabby Chic 200x200/400x400 mm/ Fabric Shabby Chic 400x400 mm

Characteristics		Test Method		
DIMENSIONS				
LENGTH AND WIDTH	W	ISO 10545-2	+/-0.5% 2 mm	
	10 test		+/-0.5% 2 mm	
THICKNESS			+/-5% +/- 0.5 mm	
STRAIGHTNESS OF SIDES			+/-0.3% +/- 1.5 mm	
RECTANGULARITY			+/-0.3% +/- 1.5 mm	
SURFACE FLATNESS			ISO 10545-2	+/-0.3% max +/- 1.5 mm
			ASTM C 485	Warpage diagonal edge +/- 0.4%
SHADE VARIATIONS				V3
WATER ABSORPTION			ISO 10545-3	10x10: E ≤ 0.5% Blb GL E ≤ 0.3% Bla GL
FROST RESISTANCE			ISO 10545-12	Frost Proof
LINEAR THERMAL EXPANSION COEFFICIENT (50°/400°)		ISO 10545-8	Test method available	
RESISTANCE TO THERMAL SHOCK		ISO 10545-9	Resistant	
CRAZING RESISTANCE OF GLAZED TILES		ISO 10545-11	Resistant	
SCRATCH HARDNESS (MOHS scale)		EN 101	MOHS > 6	
RESISTANCE TO SURFACE ABRASION OF GLAZED TILES		ISO 10545-7	Class 4	
ABRASION RESISTANCE		UNI EN ISO 10545-6	-	
RESISTANCE TO HOUSEHOLD CHEMICALS		ISO 10545-13	Class A	
RESISTANCE TO LOW CONCENTRATIONS OF ACIDS & BASES			Class A	
RESISTANCE TO STAINS OF GLAZED TILES			Class 5	
LEAD AND CADMIUM GIVEN OFF BY GLAZED TILES		ISO 10545-15	-	
BENDING STRENGTH	Modulus of Rupture	ISO 10545-4	R ≥ 35 N/mm ²	
	Breaking of Rupture		S ≥ 1300 N	
ANTI SLIP PROPERTIES / STATIC COEFFICIENT OF FRICTION		DIN 51130	R10	
		DIN 51097	Class B	
		B.C.R.A. REP. CEC. 6/81	0.40 ≤ μ ≤ 0.74	
		DCOF		


Degree of colour change:




Low
V1



Medium
V2



High
V3



Random
V4

Low V1 THE LEAST AMOUNT OF SHADE AND TEXTURE VARIATION
 Medium V2 LIGHT TO MODERATE SHADE AND TEXTURE VARIATION WITHIN EACH CARTON.
 High V3 HIGH SHADE AND TEXTURE VARIATION WITHIN EACH CARTON
 Random V4 VERY HIGH SHADE AND TEXTURE VARIATION WITHIN EACH CARTON

SLIP RESISTANCE



6°-10° 10°-19° 19°-27° 27°-35° >35°

Note: The classification gives the parameter to determine the sliding resistance. The group R9 is less anti-slip, while the group R13 has the maximum effectiveness.