

NAI WAVES BLANCO 33.3X550mm

| Characteristics   | ISO          | Result                                   |
|---|--------------|--|
| DIMENSIONAL FEATURES  | ISO 10545-2  | Complies with the standard               |
| WATER ABSORPTION  | ISO 10545-3  | 16 %                                     |
| MODULUS OF RUPTURE  | ISO 10545-4  | 600 - 900 N                              |
| BREAKING STRENGTH   |              | 15 - 25 N/mm <sup>2</sup>                |
| LINEAR THERMAL EXPANSION  | ISO 10545-8  | <7.0 x 10 <sup>-6</sup> °C <sup>-1</sup> |
| THERMAL SHOCK RESISTANCE  | ISO 10545-9  | Resists                                  |
| CRAZING RESISTANCE  | ISO 10545-11 | Resists                                  |
| CHEMICAL RESISTANCE - AMMONIUM CHLORIDE 100 G/L<br>- SODIUM HYPOCHLORITE 20 MG/L<br>- HYDROCHLORIC ACID 3%<br>- CITRIC ACID 100 G/L<br>- POTASSIUM HYDROXYDE 30 G/L | ISO 10545-13 | A  |
|   |              | A  |
|   |              | Complies with the standard               |
|   |              | Complies with the standard               |
|   |              | Complies with the standard               |
| STAIN RESISTANCE - GREEN AGENT IN LIGHT OIL<br>- IODINE SOLUTION IN ALCOHOL<br>- OLIVE OIL  | ISO 10545-14 | 5  |
|   |              | 5  |
|   |              | 5  |