

BLACK ROSE/CONCRETE BLANCO / STATUARIO PEARL 800X1600X9mm

Characteristics	Method of Test	ISO Standard	Factory Specification	
		DIS 13006	Value	Unit
DEVIATION OF AVERAGE SIZE FROM WORKING SIZE	ISO 10545-2	+/- 0.60	+ 0.03% / 0.00%	%
DEVIATION OF AVERAGE SIZE FROM THE AVERAGE OF 10 SAMPES	ISO 10545-2	+/- 0.50	+ 0.01% / - 0.00%	%
THICKNESS	ISO 10545-2	+/- 5.0	+ 0.74% / - 0.00%	%
STRAIGHTNESS OF SIDES 60 MM	ISO 10545-2	+/- 0.50	+ 0.02% / - 0.03%	%
STRAIGHTNESS OF SIDES 120 MM		+/- 0.50	+ 0.02% / - 0.03%	%
RECTANGULARITY	ISO 10545-2	+/- 0.60	+ 0.03% / - 0.04%	%
CENTRE CURVATURE, RELATED TO DIAGONAL CALCULATED FROM THE WORK SIZES	ISO 10545-2	+/- 0.50	+ 0.03% / - 0.00%	%
EDGE CURVATURE, RELATED TO THE SMALLEST SIZE OF THE TILE	ISO 10545-2	+/- 0.50	+ 0.04% / - 0.00%	%
EDGE CURVATURE, RELATED TO THE BIGGEST SIZE OF THE TILE	ISO 10545-2	+/- 0.50	+ 0.04% / - 0.00%	%
SURFACE QUALITY	ISO 10545-2	> = 95	96%	%
WATER ABSORPTION % BY WEIGHT	ISO 10545-3	< = 0.5	0.05%	%
MODULUS OF RUPTURE	ISO 10545-4	> = 35	60.71	N/mm ²
BREAKING STRENGTH	ISO 10545-4	> = 1300	3540.81	N
RESISTANCE TO STAINING	ISO 10545-14	Min. Class 3	Class 5	-