

MOZ ALL COLOURS FULL BODY MATT 600x600/600x1200mm

Size:	600 x 600 mm 600 x 1200 mm
Material:	Full Body Porcelain
Finish:	Matt
Number of faces:	Temporarily Unknown

Characteristics	ISO	Standard as per ISO-13006/EN176 Group Bla	Mean Value Full Body Vitrified Tiles
DEVIATION IN LENGTH AND WIDTH	ISO 10545-2	+/- 0.60 %	+/- 0.10 %
DEVIATION IN THICKNESS	ISO 10545-2	+/- 5.00 %	+/- 2.00 %
STRAIGHTNESS OF SIDES	ISO 10545-2	+/- 0.50 %	+/- 0.10 %
RECTANGULARITY	ISO 10545-2	+/- 0.60 %	+/- 0.10 %
SURFACE FLATNESS	ISO 10545-2	+/- 0.50 %	+/- 0.10 %
GLOSSINESS	Gloss Meter	Gloss Meter	Min. 90 %
WATER ABSORPTION	ISO 10545-3	≤ 0.50 %	E ≤ 0.05 %
BREAKING STRENGTH	ISO 10545-4	1300 N	2000 N
ABRASION RESISTANCE	ISO 10545-6	Max. 175mm	Max. 145mm ³
MOH's HARDNESS	EN 101	Min. 6	≥ 6*
FROST RESISTANCE	ISO 10545-12	Frost Proof	Frost Proof
THERMAL SHOCK	ISO 10545-9	No Damage	No Damage
MOISTURE EXPANSION	ISO 10545-10	Nil	Nil
THERMAL EXPANSION	ISO 10545-8	< 9 x 10 ⁻⁶	< 6 x 10 ⁻⁶
RESISTANCE OF HOUSEHOLD CHEMICALS	ISO 10545-13	No Damage	No Damage*
MODULUS OF RUPTURE (MOR)	ISO 10545-4	Min 35 Individual Min 32	Average: 46.52 N/mm ² Minimum 39.81 N/mm ²
STAIN RESISTANCE	ISO 10545-14	Resistance	Resistance*
SLIP RESISTANCE (Friction Co-Efficient) (DRY)	ISO 10545-17	> 0.40	> 0.40
SLIP RESISTANCE (RAMP TEST)	DIN 51130	R9	R9

SLIP RESISTANCE



Note: The classification gives the parameter to determine the sliding resistance. The group R9 is less anti-slip, while the group R13 has the maximum effectiveness.